



## HARDOX 500 PLATE



## HARDOX 500 PLATE

### General Product Description

The bendable, weldable and highly abrasion-resistant steel.

Hardox 500 is a bendable and weldable abrasion-resistant steel, with a nominal hardness of 500 HBW. Suitable for applications that demand higher wear resistance.

Hardox 500 increases payload and increases service life while maintaining good processability and toughness.

### Dimension Range

Hardox 500 is available in thicknesses of 4.0 – 103 mm. Hardox 500 is available in widths up to 3350 mm and lengths up to 14630 mm. More detailed information on dimensions is provided in the dimension program.

### Mechanical Properties

Thickness (mm)	Hardness <sup>1)</sup> (HBW)	Typical yield strength (MPa), not guaranteed
4.0- 32.0	470- 530	1250- 1400
32.1- 103.0	450- 540	1250- 1400

<sup>1)</sup> Brinell hardness, HBW, according to EN ISO 6506-1, on a milled surface 0.5 – 3 mm below surface. At least one test specimen per heat and 40 tons. The nominal material thickness will not deviate more than ± 15 mm from that of the test specimen.

Hardox is through-hardened. Minimum core hardness is 90 % of the guaranteed minimum surface hardness.

### Impact Properties

Grade	Longitudinal test, typical impact energy, Charpy V 10x10 mm test specimen.
Hardox 500 <sup>1)</sup>	37 J/-40 °C

<sup>1)</sup> Impact toughness measured upon agreement. For thicknesses between 6 - 11.9 mm, subsize Charpy V-specimens are used. The specified toughness is then proportional to the cross-sectional area of the test specimen, compared to a full-size specimen (10 x 10 mm). Impact testing according to ISO EN 148. Average of three tests.

# HARDOX 500 PLATE

## Chemical Composition (heat analysis)

C <sup>*)</sup> (max %)	Si <sup>*)</sup> (max %)	Mn <sup>*)</sup> (max %)	P (max %)	S (max %)	Cr <sup>*)</sup> (max %)	Ni <sup>*)</sup> (max %)	Mo <sup>*)</sup> (max %)	B <sup>*)</sup> (max %)
0.30	0.70	1.60	0.020	0.010	1.50	1.50	0.60	0.005

The steel is grain refined. <sup>\*)</sup> Intentional alloying elements.

## Carbon Equivalent CET(CEV)

Thickness (mm)	4.0 - 13.0	13.1 - 19.9	20.0 - 39.9	40.0 - 103.0
Max CET(CEV)	0.38 (0.53)	0.43 (0.64)	0.45 (0.66)	0.47 (0.75)
Typ CET(CEV)	0.37 (0.51)	0.41 (0.63)	0.41 (0.63)	0.43 (0.72)

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

## Tolerances

More details are given in SSAB's brochure 41-General Product Information Strenx, Hardox, Armox and Toolox-UK and Hardox® Guarantees or at [www.ssab.com](http://www.ssab.com).

### Thickness

Tolerances according to Hardox Thickness Guarantees. Hardox® Guarantees meets the requirements of EN 10 029 Class A.

### Length and Width

According to SSAB's dimension program. Tolerances according to SSAB's mill edge standards or tolerances that conform to EN 10 029.

### Shape

Tolerances according to EN 10 029.

### Flatness

Tolerances according to Hardox Flatness Guarantees Class D, which are more restrictive than EN 10 029.

### Surface Properties

According to EN 10 163-2, Class A Subclass 1.

### Bending

Tolerances are according to Hardox Bending Guarantees Class F.

# HARDOX 500 PLATE

## Delivery Conditions

The delivery condition is Q or QT (Quenched or Quenched and Tempered). The plates are delivered with sheared or thermally cut edges. Thicknesses over 80 mm are delivered with mill edge as standard. Delivery requirements can be found in SSAB's brochure 41-General product information Strenx, Hardox, Armox and Toolox-UK or at [www.ssab.com](http://www.ssab.com).

## Fabrication and Other Recommendations

### **Welding, bending and machining.**

Recommendations can be found in SSAB's brochures at [www.hardox.com](http://www.hardox.com) or consult Tech Support, [techsupport@ssab.com](mailto:techsupport@ssab.com).

Hardox 500 is not intended for further heat treatment. It has obtained its mechanical properties by quenching and when necessary by means of subsequent tempering. The properties of the delivery condition cannot be retained after exposure to temperatures in excess of 250°C .

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on this product. Grinding, especially of primer coated plates, may produce dust with a high particle concentration.



The UK English version of this document shall prevail in case of discrepancy. Download the latest version of this document at [www.ssab.com](http://www.ssab.com)  
Hardox, Strenx, Docol, Dogal, Domex, Toolox, Laser, Armox, Ramor, GreenCoat are trademarks of SSAB Technology AB, Sweden